

FSE323L

LOW-VISCOSITY FIBRE-SATURATING EPOXY RESIN FOR HEAVY-WEIGHT CARBON FIBRE FABRIC APPLICATIONS

60 MPa

TENSILE STRENGTH

3.1 GPa

ELASTIC MODULUS

3 : 1

MIX RATIO (BY WEIGHT)

50 min

POT LIFE (23 °C)

DESCRIPTION

FSE323L is a two-component, low-viscosity epoxy resin engineered for complete saturation of heavy-weight carbon fibre fabrics ($\geq 300 \text{ g/m}^2$). Its viscosity below $500 \text{ mPa}\cdot\text{s}$ at $25 \text{ }^\circ\text{C}$ allows rapid and thorough fibre wet-out, minimising dry spots and voids even in multi-layer laminate build-ups with 600 g/m^2 fabrics. The 3 : 1 mix ratio by weight provides a simple, reliable batching process.

INTENDED USES

- Complete impregnation of heavy-weight ($300\text{--}600 \text{ g/m}^2$) FIDSTRONG FSC-series carbon fibre fabrics
- Multi-layer wet lay-up where rapid resin absorption is critical for laminate quality
- Flexural, shear, and confinement strengthening of reinforced concrete and masonry elements
- Seismic retrofit and structural rehabilitation of columns, beams, walls, and slabs
- Multi-layer laminate build-up for high-demand flexural or confinement applications

CHARACTERISTICS

- Ultra-low viscosity ($< 500 \text{ mPa}\cdot\text{s}$ at $25 \text{ }^\circ\text{C}$) — rapid, void-free wet-out of heavy-weight and multi-layer fabrics
- High mechanical properties — 60 MPa tensile strength, 3.1 GPa modulus for effective stress transfer
- 3 : 1 mix ratio by weight — simple batching with clearly colour-coded components
- 50 min pot life at $23 \text{ }^\circ\text{C}$ — balanced working time for multi-layer applications
- Solvent-free, VOC-compliant — suitable for enclosed and occupied spaces
- Typical consumption: $0.7\text{--}0.9 \text{ kg/m}^2$ for 300 gsm fabric, $1.0\text{--}1.2 \text{ kg/m}^2$ for 600 gsm fabric

PRODUCT INFORMATION

PROPERTY	VALUE
Appearance	Component A + B mixed: blue
Mix Ratio	A : B = 3 : 1 by weight
Packaging	24 kg (A) + 8 kg (B) per kit, or customised packaging
Storage	Dry, away from direct sunlight, $+5 \text{ }^\circ\text{C}$ to $+35 \text{ }^\circ\text{C}$
Shelf Life	18 months in original, unopened packaging

TECHNICAL PROPERTIES

MIXED / CURED RESIN — TESTED AT $23 \text{ }^\circ\text{C}$ / 50 % RH UNLESS STATED

PROPERTY	TEST METHOD	VALUE
----------	-------------	-------

PROPERTY	TEST METHOD	VALUE
HANDLING (MIXED RESIN)		
Pot Life (500 g mass)	—	50 min
Touch-Dry Time	—	1.5 h
Full Cure	—	7 days
Service Temperature	—	-5 °C to +40 °C
Viscosity (mixed)	—	< 500 mPa·s (25 °C)
Thixotropic Index	—	N/A (low - viscosity formulation)
Non-volatile Content	—	≥ 99.5 %
MECHANICAL (CURED, 7 DAYS)		
Tensile Strength	ASTM D638	60 MPa
Tensile Elastic Modulus	ASTM D638	3.1 GPa
Elongation at Break	ASTM D638	2.3 %
Flexural Strength	ASTM D790	81 MPa
Compressive Strength	ASTM D695	90 MPa
ADHESION (CURED)		
Steel-to-Steel Tensile	—	≥ 40 MPa
Steel-to-Steel Shear	ASTM D1002	≥ 14 MPa
Bond to Concrete (pull-off)	ASTM C882	≥ 2.5 MPa (concrete failure)

CONSUMPTION

FABRIC WEIGHT	PRIMER COAT (FSE302)	SATURATING COAT / LAYER
200 g/m ²	0.3–0.4 kg/m ²	0.5–0.7 kg/m ²
300 g/m ²	0.3–0.4 kg/m ²	0.6–0.9 kg/m ²
600 g/m ²	0.3–0.4 kg/m ²	1.0–1.2 kg/m ²

Actual consumption depends on substrate porosity and surface profile. A trial application is recommended.

COMPATIBLE SYSTEM PRODUCTS

CODE	FUNCTION	NOTES
FSE302	Substrate primer	Adhesion-promoting epoxy primer; 2 : 1 mix ratio by weight
FSE502	Levelling adhesive	Substrate repair and surface regularisation before priming
FSC series	Carbon fibre fabrics	200 / 300 / 600 g/m ² unidirectional; multiple strength grades

APPLICATION INSTRUCTIONS

Step 1 — Surface Preparation

-
- Fill cavities and surface irregularities > 1 mm with FSE502 levelling adhesive; allow full cure before proceeding.

Step 2 — Priming

- Apply FSE302 primer by brush or roller; ensure uniform coverage and full absorption into the substrate pore structure.
- Over-coat once primer is tack-free (typically 2–4 h at 23 °C) but before full cure.

Step 3 — Mixing

- Combine A : B at 3 : 1 by weight; mix with a low-speed paddle mixer for 3 min until a uniform colour is achieved. Use within the pot life.

Step 4 — Fabric Saturation and Bonding

- Apply a base coat to the primed substrate (0.3–0.4 kg/m²). Place pre-cut FSC fabric onto the wet resin.
- Roll firmly with a ribbed roller from centre outward to eliminate air and ensure full fibre wet-out. Apply saturating coat through the fabric until all fibres are encapsulated.
- For multi-layer applications, repeat the lay-up while the previous layer is still tacky.

Step 5 — Curing and Protection

- Protect from traffic and direct sunlight during cure (7 days at 23 °C). Apply a UV-protective top-coat or cementitious render after full cure.

LIMITATIONS

- Application temperature: +5 °C to +35 °C (substrate and ambient). Do not apply to standing-water surfaces.
- Substrate moisture content ≤ 4 % (ASTM D4263).
- All structural design must be prepared and certified by a licensed professional engineer (ACI 440.2R or equivalent).

HEALTH & SAFETY

NOTE

Refer to the current Safety Data Sheet (SDS) for handling, storage, and disposal. Wear chemical-resistant gloves, safety goggles, and respiratory protection in poorly ventilated areas. This TDS does not replace the SDS.

LEGAL NOTES

The information and recommendations in this document are given in good faith based on current knowledge and experience of the products when properly stored, handled, and applied under normal conditions. Differences in materials, substrates, and site conditions mean that no warranty in respect of merchantability or fitness for a particular purpose can be inferred from this information. The information does not relieve the user of the responsibility of testing products for their intended application. All orders are accepted subject to our current terms of sale and delivery. Refer to the most recent TDS at www.fidstrong.com.